



105 Epoxy Resin® / 206 Slow Hardener®

Technical Data Sheet

105 System 105/206

General Description

105/206 Epoxy is used for general coating and bonding applications when extended working and cure time are needed or to provide adequate working time at higher temperatures.

105/206 forms a high-strength, moisture-resistant solid with excellent bonding and barrier coating properties. It will wet out and bond to wood fiber, fiberglass, reinforcing fabrics, foam and other composite materials, and a variety of metals.

105/206 Epoxy can be thickened with WEST SYSTEM fillers to bridge gaps and fill voids and can be sanded and shaped when cured. With roller applications, it has excellent thin-film characteristics, allowing it to flow out and self-level without “fish-eyeing.” Multiple coats of 105/206 Epoxy create a superior moisture barrier and a tough, stable base for paints and varnishes. It is formulated without volatile solvents resulting in a very low VOC content. It has a relatively high flash point, no strong solvent odor and does not shrink after curing. It is not intended for clear coating natural finished wood.

Handling Characteristics

Mix ratio by volume (300 Mini Pump ratio)	5 parts resin : 1 part hardener
by weight.....	5.36 : 1
Acceptable ratio range by weight	4.84 : 1 to 6.19 : 1
Mix viscosity (at 72°F) ASTM D-2393	725 cps
Pot life (100g at 72°F)	20 to 25 minutes
Working time, thin film*	90 to 110 minutes
Cure to a solid, thin film*	10 to 15 hours
Cure to working strength	1 to 4 days
Minimum recommended temperature	60°F (16°C)

**Epoxy cures faster at higher temperatures and in thicker applications.*

Physical Properties of Cured Epoxy

Specific gravity	1.18
Hardness (Shore D) ASTM D-2240	83
Compression yield ASTM D-695	11,500 psi
Tensile strength ASTM D638	7,300 psi
Tensile elongation ASTM D-638	4.5%
Tensile modulus ASTM D-638	4.60E+05 psi
Flexural strength ASTM D-790	11,800 psi
Flexural modulus ASTM D-790	4.50E+05
Heat deflection temperature ASTM D-648.....	123°F
Onset of Tg by DSC	126°F
Ultimate Tg	139°F

Storage/Shelf Life

Store at room temperature. Keep containers closed to prevent contamination. With proper storage, resin and hardeners should remain usable for many years. After a long storage, verify the metering accuracy of the pumps. Mix a small test batch to assure proper curing.

Over time, 105 Resin will thicken slightly and will therefore require extra care when mixing. Repeated freeze/thaw cycles during storage may cause crystallization of 105 Resin. Warm resin to 125°F and stir to dissolve crystals. Hardener may darken with age, but physical properties are not affected by color. Be aware of a possible color shift if very old and new hardener are used on the same project.

Gougeon Brothers, Inc.
P.O. Box 908
Bay City, MI 48707

866-937-8797

westsystem.com